



PRODUCT DATA SHEET

Clear CAB Acrylic Lacquers

CAB-0090 Gloss (90°) CAB-0030 Satin (30°)
 CAB-0060 Semi-Gloss (60°) CAB-0010 Flat (10°)

DESCRIPTION	CHARACTERISTICS	SPECIFICATIONS
<p>A high performance clear CAB acrylic lacquer. It has a proven track record in Industrial use for high quality cabinets, furniture and fixtures. This lacquer can be applied over stained or natural wood or over a high quality sanding sealer.</p> <p>Product Advantages:</p> <ul style="list-style-type: none"> ➤ Outstanding Mar & Chemical Resistance ➤ High Build with Fewer Coats ➤ Water clear ➤ UV resistant ➤ Ready to spray ➤ Easy to Use ➤ Non Photo Chemically Reactive ➤ Phthalate Free 	<p>Viscosity: 14" #4 Ford</p> <p>Weight Solids: 20-21%</p> <p>Volume Solids: 16-17%</p> <p>Weight/Gallon: 7.43-7.48 lbs/gal</p> <p>Film Hardness: B Overnight</p> <p>VOC (Reg/coating): 5.62 lbs/gal or 674 g/l</p> <p>VOC (Act./material): 4.17 lbs/gal or 500 g/l</p> <p>HAPs: .8250-.8357 lbs haps/lbs gal</p> <p>Coverage: 270-277 sq ft per gallon at one mil dry film thickness</p> <p>Dry Time: 6 minutes <i>(Note: relative humidity and temperature will effect dry time)</i></p> <p>Shelf Life: 12 months if unopened and stored in a cool dry area. Always rotate stock.</p> <p><i>Note: These numbers represent actual control values on a smooth, sanded substrate. Spray techniques, texture, and sealing as well as film thickness may give different results on actual work, but they may be used for comparison. To the best of our knowledge, the above technical data is true and accurate at the date of issuance but is subject to change without prior notice.</i></p>	<p>Surface Preparation: New wood: Remove any dirt, grease, glue or other contaminants and sand wood as required. Moisture content of wood should be 7-9%. Old wood: Strip old finishes completely and remove all contaminants from the surface. Make sure the surface is dry, sand as required. Finish as new work.</p> <p>Material Preparation: All wood surfaces must be dry, clean, and free of contaminates.</p> <p>Application: We recommend a coating system comprised of one coat of sealer applied at 3-4 mils wet film build and 1-2 coats of topcoat applied at 3-4 mils wet film build. Apply with conventional, air assisted airless, HVLP or airless equipment.</p> <p>Clean Up: Use SOL-9011 Non HAPS Thinner to clean all equipment. Dispose of in accordance with Federal, State, and Local regulation regarding pollution.</p>

The following supersedes any provision contained in the forms, letters and papers of your company. This product is designed and intended for professional application only. All products should be thoroughly tested under application conditions prior to use. The information contained herein is believed to be reliable. **HOWEVER, GEMINI MAKES NO WARRANTY CONCERNING THIS PRODUCT, WHETHER EXPRESS OR IMPLIED, INCLUDING THE WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE.** UNDER NO CIRCUMSTANCES SHALL GEMINI BE LIABLE FOR SPECIAL, INCIDENTAL, CONSEQUENTIAL, OR ANY OTHER DAMAGES FROM ALLEGED NEGLIGENCE, BREACH OF WARRANTY, STRICT LIABILITY, OR ANY OTHER LEGAL THEORY, ARISING OUT OF THE USE OR HANDLING OF THIS PRODUCT. THE SOLE REMEDY OF THE BUYER AND THE SOLE LIABILITY OF GEMINI FOR ANY CLAIMS SHALL BE LIMITED TO THE BUYER'S PURCHASE PRICE OF THE PRODUCT WHICH IS THE SUBJECT OF THE CLAIM OR THE AMOUNT ACTUALLY PAID FOR SUCH PRODUCT, WHICHEVER IS LESS. TECHNICAL ADVICE FURNISHED BY GEMINI SHALL NOT CONSTITUTE AN EXPRESS WARRANTY, WHICH IS EXPRESSLY DISCLAIMED. ALL TECHNICAL ADVICE GIVEN IS ACCEPTED AT THE RISK OF THE BUYER.

CAUTION: DANGER! FLAMMABLE! VAPORS MAY CAUSE FLASH FIRE. VAPOR HARMFUL. HARMFUL OR FATAL IF SWALLOWED. INJURIOUS TO EYES. KEEP OUT OF THE REACH OF CHILDREN! BEFORE using this product it is essential that the "Material Safety Data Sheet" describing the product as well as the "Product Label" be reviewed. If your company does not have such information or has any questions, contact the manufacturer.

Date: May 2010

The **KCMA (Kitchen Cabinet Manufacturers Association)** test was conducted with the test panel in a vertical position. Each test panel was prepared as specified in the application instructions above. 3cc's of each chemical were placed on the coated surface and allowed to remain there for a period of 24 hours, with the exception of mustard, which was removed from the panel after one hour.

The **ASTM (American Society for Testing Materials)** test was conducted with the test panel in a horizontal position. Each test panel was coated as specified in the application instructions above. 3cc's of each chemical were placed on the coated surface and contained there by the use of a watch glass for a period of sixteen hours unless otherwise indicated.

The **AWI (Architectural Woodwork Institute) Chemical Resistance Test** is conducted by containing the test panel in a horizontal position while applying 1 milliliter of various chemicals to the surface of the coating. Each chemical is maintained at its respective location on the panel by the use of a watch glass. All chemicals are allowed to remain in contact with the coating surface for a period of 16 hours unless otherwise indicated.

Each chemical is then evaluated for its impact upon the coated surface, which includes such parameters as loss of gloss, discoloration, blistering, and delamination. The chemicals used and their respective effects upon the coating are as follows:

	KCMA Test		ASTM Test		AWI Test	
	Initial Results	Final Results	Initial Results	Final Results	Initial Results	Final Results
Catsup	No Damage	No Damage	No Damage	No Damage	N/A	N/A
Vinegar	No Damage	No Damage	No Damage	No Damage	N/A	N/A
Alcohol	No Damage	No Damage	No Damage	No Damage	N/A	N/A
Olive Oil	No Damage	No Damage	No Damage	No Damage		
2% Ammonia	No Damage	No Damage	No Damage	No Damage	N/A	N/A
Lemon Juice	No Damage	No Damage	No Damage	No Damage		
Coffee	No Damage	No Damage	No Damage	No Damage		
Mustard	No Damage	No Damage	No Damage @ 15 minutes	No Damage		
Water	No Damage	No Damage	No Damage	No Damage	N/A	N/A
Motor Oil	N/A	N/A	No Damage	No Damage	N/A	N/A
Lighter Fluid	N/A	N/A	No Damage	No Damage	N/A	N/A
1% Palmolive Solution	N/A	N/A	No Damage	No Damage		
1% Tide Solution	N/A	N/A	No Damage	No Damage	N/A	N/A
4% Sodium Hydroxide	N/A	N/A	N/A	N/A		
10% Sodium Hydroxide	N/A	N/A	N/A	N/A		
28% Ammonia	N/A	N/A	N/A	N/A		
10% Sodium Phosphate	N/A	N/A	N/A	N/A		
95% Ethyl Alcohol	N/A	N/A	N/A	N/A		
Tomato Juice	N/A	N/A	N/A	N/A		
50% Sulfuric Acid	N/A	N/A	N/A	N/A		
Nail Polish Remover	N/A	N/A	N/A	N/A		
Glacial Acetic Acid	N/A	N/A	N/A	N/A		

KCMA 9.2 Hot and Cold Check Resistance Test:

All panels passed 21 cold check cycles (cycling from 120 °F. to -5°F. and 70% Relative Humidity to zero Relative Humidity).

KCMA 10.0 Detergent Water Resistance Test:

Passes 24 hours