



PRODUCT DATA SHEET

Titanium Clear High Solids Acrylic / Urethane Modified Waterborne

WB-0290 Gloss (90°) WB-0230 Satin (30°)
WB-0260 Semi-Gloss (60°) WB-0210 Flat (10°)

DESCRIPTION	CHARACTERISTICS	SPECIFICATIONS
<p>Titanium Clear Waterborne High Solids Acrylic coatings are a single component, acrylic / urethane modified, high solids waterborne coatings system containing low levels of solvent allowing for reduction in VOCs and HAPs. Utilizing the latest waterborne technology, this system can be used as an introductory performance coating in areas where extreme water and chemical resistance are not necessary. It is water clear and non-yellowing. Apply two or three coats, self-sealing, or if a sealer is desired, use two coats of WBS-0100 Titanium Clear Waterborne Sealer and one topcoat. This product meets all of the pertinent government regulations regarding emissions and meets or exceeds the performance parameters outlined by KCMA and ASTM</p> <p>Product Advantages:</p> <ul style="list-style-type: none"> ➤ Low Odor ➤ Sealer Provides Excellent Sandability ➤ Quick Dry ➤ Quick Stack Time ➤ Excellent Film Building Properties ➤ Excellent Flow and Leveling ➤ Minimum Grain Raise ➤ Resists Yellowing* ➤ Durable Moisture and Chemical Resistant Film ➤ Meets KCMA and ASTM Performance Requirements, When Applied to Manufacturer's Specifications <p><small>* The coating will not protect the wood, lightly stained wood substrates or pigmented basecoats from yellowing</small></p>	<p>Viscosity: 30"-35" #3 Zahn @ 77°</p> <p>Weight Solids: 33.5%</p> <p>Volume Solids: 30%</p> <p>Weight/Gallon: 8.49 lbs/gal</p> <p>VOC (Act./material): 0.5 lbs/gal (less exempt solvents)</p> <p>Coverage: 460 sq ft per gallon at one mil dry film thickness.</p> <p>Dry Time: Tack free in 15-20 minutes, sand in 45 minutes, stack in 4 hours. <i>(Note: relative humidity and temperature will effect dry time)</i></p> <p>Shelf Life: 6 months in a properly sealed container. Always rotate stock.</p> <p>Protect product from freezing.</p> <p style="text-align: center;"><small><i>Note: These numbers represent actual control values on a smooth, sanded substrate. Spray techniques, texture, and sealing as well as film thickness may give different results on actual work, but they may be used for comparison. To the best of our knowledge, the above technical data is true and accurate at the date of issuance but is subject to change without prior notice.</i></small></p>	<p>Surface Preparation: New wood: Remove any dirt, grease, glue or other contaminants and sand wood as required. Moisture content of wood should be 7-9%. Old wood: Strip old finishes completely and remove all contaminants from the surface. Make sure the surface is dry, sand as required. Finish as new work.</p> <p>Material Preparation: Mix thoroughly before use. Reduction may be required for certain types of application. Water should be used for reduction, not to exceed 15% by volume. If a slower dry time is desired, use Butyl Carbitol.</p> <p>Application: Temperature will effect viscosity. Titanium Waterborne coatings are designed for spray application. This product must not be polluted with oil, solvent based paint or the like and should not be applied to metal surfaces. Application and drying conditions must be at temperatures of 64°F or above and at a humidity of less than 65%. Increased air flow and/or drying temperatures, including the use of infrared lighting for cure will significantly decrease dry times. Further coats may be applied followed by sanding with 280/320-grit sandpaper. Maximum dry film thickness should not exceed 4 mils.</p> <p>Clean Up: Use water to clean all equipment when material is in a liquid stage. Use an 80/20 blend of water/Butyl Carbitol when material is partially cured. Use Acetone to remove dried coating.</p>

The following supersedes any provision contained in the forms, letters and papers of your company. This product is designed and intended for professional application only. All products should be thoroughly tested under application conditions prior to use. The information contained herein is believed to be reliable. **HOWEVER, GEMINI MAKES NO WARRANTY CONCERNING THIS PRODUCT, WHETHER EXPRESS OR IMPLIED, INCLUDING THE WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE.** UNDER NO CIRCUMSTANCES SHALL GEMINI BE LIABLE FOR SPECIAL, INCIDENTAL, CONSEQUENTIAL, OR ANY OTHER DAMAGES FROM ALLEGED NEGLIGENCE, BREACH OF WARRANTY, STRICT LIABILITY, OR ANY OTHER LEGAL THEORY, ARISING OUT OF THE USE OR HANDLING OF THIS PRODUCT. THE SOLE REMEDY OF THE BUYER AND THE SOLE LIABILITY OF GEMINI FOR ANY CLAIMS SHALL BE LIMITED TO THE BUYER'S PURCHASE PRICE OF THE PRODUCT WHICH IS THE SUBJECT OF THE CLAIM OR THE AMOUNT ACTUALLY PAID FOR SUCH PRODUCT, WHICHEVER IS LESS. TECHNICAL ADVICE FURNISHED BY GEMINI SHALL NOT CONSTITUTE AN EXPRESS WARRANTY, WHICH IS EXPRESSLY DISCLAIMED. ALL TECHNICAL ADVICE GIVEN IS ACCEPTED AT THE RISK OF THE BUYER.

CAUTION: DANGER! FLAMMABLE! VAPORS MAY CAUSE FLASH FIRE. VAPOR HARMFUL. HARMFUL OR FATAL IF SWALLOWED. INJURIOUS TO EYES. KEEP OUT OF THE REACH OF CHILDREN! BEFORE using this product it is essential that the "Material Safety Data Sheet" describing the product as well as the "Product Label" be reviewed. If your company does not have such information or has any questions, contact the manufacturer.

Date: Dec-06